


TECH SPEC SHEET

Playa Model

www.proflowpavers.com



Features - Summary Description

Lightweight for rooftop and pedestrian walkway applications. Tight voidspace to allow for ideal foot traffic and average permeability.

Physical Specification

Dry Weight Lbs	5 3/4
Dimensions In	1 7/8" x 1 7/8" x 2 2/5"
Block Count	25
Total Coverage Sqft	1
Physical Dimension Sqf	7/10

Installation Specifications

Pavers per Sqft	1
Gap Space In	2.54
Void Space Ft3	0.39
Romex Filler Lbs	2 1/2
Total Pavers Per Pallet	144
Pallet Weight Lbs	992
Pallet Dimensions In (W x L x H)	48 x 40 x 40

Material Specification (Wood)

COMMON NAME	BLACK LOCUST		
Color	Pale yellow to dark brown	Modulus of Elasticity	14,14 GPa
Scientific Name	Robinia Pseudoacacia	Maximum Crushing Strength	70.3 MPa
Grain	Tight Grain	Janka Hardness	7560 N
Density @ 12% Moisture	.66	Modulus of Rupture	133.8 MPa
Free Of Heart Center			

Environmental Benefits

Carbon Sequestered Per Paver 1179.46 g Carbon



BIOFILTRATION



STORMWATER MANAGEMENT



HEAT ISLAND EFFECT



CHEMICAL FREE

Product Benefits



WARRANTY



PET FRIENDLY



ROT RESISTANT



FROST RESISTANT




PERMEABILITY

TECH SPEC SHEET

Playa Model

www.proflowpavers.com



Features - Summary Description

Lightweight for rooftop and pedestrian walkway applications. Tight voidspace to allow for ideal foot traffic and average permeability.

Physical Specification

Dry Weight KG	2.6
Dimensions Cm	4.8 x 4.8 x 6
Block Count	25
Total Coverage Cm2	29
Physical Dimension Cm	27

Installation Specifications

Pavers per Sq Meter	13.22
Gap Space Cm	01
Void Space M3	0.018085
Romex Filler Grams	1100
Total Pavers Per Pallet	288
Pallet Weight KG	450
Pallet Dimensions cm (W x L x H)	90 x 120 x 94

Material Specification (Wood)

COMMON NAME		BLACK LOCUST	
Color	Pale yellow to dark brown	Modulus of Elasticity	14,14 GPa
Scientific Name	Robinia Pseudoacacia	Maximum Crushing Strength	70.3 MPa
Grain	Tight Grain	Janka Hardness	7560 N
Density @ 12% Moisture	.66	Modulus of Rupture	133.8 MPa
Free Of Heart Center			

Environmental Benefits

Carbon Sequestered Per Paver 1179.46 g Carbon



BIOFILTRATION



STORMWATER MANAGEMENT



HEAT ISLAND EFFECT



CHEMICAL FREE

Product Benefits



WARRANTY



PET FRIENDLY



ROT RESISTANT



FROST RESISTANT




PERMEABILITY

TECH SPEC SHEET

Playa Model (half size)

www.proflowpavers.com



Features - Summary Description

Lightweight for rooftop and pedestrian walkway applications. Tight voidspace to allow for ideal foot traffic and average permeability.

Physical Specification

Dry Weight Lbs	2.86
Dimensions In	1 7/8" x 1 7/8" x 1 1/5"
Block Count	25
Total Coverage Sqft	1
Physical Dimension Sqft	3/4

Installation Specifications

Pavers per Sqft	1
Gap Space In	2.54
Void Space Ft3	1/3
Romex Filler Lbs	2 2/5
Total Pavers Per Pallet	288
Pallet Weight Lbs	992
Pallet Dimensions In (W x L x H)	48 x 40 x 40

Material Specification (Wood)

COMMON NAME		BLACK LOCUST	
Color	Pale yellow to dark brown	Modulus of Elasticity	14,14 GPa
Scientific Name	Robinia Pseudoacacia	Maximum Crushing Strength	70.3 MPa
Grain	Tight Grain	Janka Hardness	7560 N
Density @ 12% Moisture	.66	Modulus of Rupture	133.8 MPa
Free Of Heart Center			

Environmental Benefits

Carbon Sequestered Per Paver 570.98 g Carbon



BIOFILTRATION



STORMWATER MANAGEMENT



HEAT ISLAND EFFECT



CHEMICAL FREE

Product Benefits



WARRANTY



PET FRIENDLY



ROT RESISTANT



FROST RESISTANT




PERMEABILITY

TECH SPEC SHEET

Playa Model (half size)

www.proflowpavers.com



Features - Summary Description

Lightweight for rooftop and pedestrian walkway applications. Tight voidspace to allow for ideal foot traffic and average permeability.

Physical Specification

Dry Weight KG	1.3
Dimensions Cm	4.8 x 4.8 x 3
Block Count	25
Total Coverage Cm2	29
Physical Dimension Cm	27

Installation Specifications

Pavers per Sq Meter	13.22
Gap Space Cm	01
Void Space M3	0.0090425
Romex Filler Grams	1100
Total Pavers Per Pallet	288
Pallet Weight KG	450
Pallet Dimensions cm (W x L x H)	90 x 120 x 94

Material Specification (Wood)

COMMON NAME		BLACK LOCUST	
Color	Pale yellow to dark brown	Modulus of Elasticity	14,14 GPa
Scientific Name	Robinia Pseudoacacia	Maximum Crushing Strength	70.3 MPa
Grain	Tight Grain	Janka Hardness	7560 N
Density @ 12% Moisture	.66	Modulus of Rupture	133.8 MPa
Free Of Heart Center			

Environmental Benefits

Carbon Sequestered Per Paver 570.98 g Carbon



BIOFILTRATION



STORMWATER MANAGEMENT



HEAT ISLAND EFFECT



CHEMICAL FREE

Product Benefits



WARRANTY



PET FRIENDLY



ROT RESISTANT



FROST RESISTANT



PERMEABILITY